

TRIDENT FOAMS LIMITED



~~X~~TRIPOR ~~X~~TRICAST ~~X~~TANCAST ~~X~~AUToFROTH ~~X~~AUtoPOR ~~X~~MHD

TRICAST 4 POLYURETHANE FOAM

DESCRIPTION

Tricast 4 rigid polyurethane medium density rigid polyurethane foam available in sheet form, and is suitable for a wide variety G.R.P. laminating applications and panel manufacturing. Tricast 4 does not contain any substances alleged to deplete the Ozone Layer, i.e. it is ODP-zero.

DIMENSIONS

Thickness: 6 - 300mm
Width: 600, 1200mm
Length: 600, 1200, 2400
Other sizes on request.

TECHNICAL PROPERTIES

Nominal density	64kg/m ³ (4lb/ft ³)
Initial thermal conductivity	0.03W/m ⁰ K@23°C(BS874, Anacon)
Closed Cell (BS4370 Prt 2 Method 10) minimum	95%
Compressive Strength (BS.4370 Prt.1 1968 Method 3)	
Normal to major plane	540 kPa
Parallel to major plane	420 kPa
Tensile Strength (BS.4370 Prt.2 1973 Method 9)	
Parallel to major plane	-
Cross break strength (BS 4370 Prt.1 method 4)	
Perpendicular to major plane	744 kPa
Shear Strength (BS.4370 Prt.2 1973 Method 6)	
Parallel to major plane	380 kPa
Upper temperature limit	70°C
Dimensional stability (BS 4370 Prt.1 method 5A)	
70°C for 7 days	<+0.5%
50°C / 100%rh for 7days	<+0.5%
-20°C for 7 days	No change

APPLICATIONS

Doors & panels, GRP manufacture - tanks, cabinets, sections and shaping, withstanding the application of glass & resin at lamination stage.

Whilst the information above is true and accurate to the best of our knowledge and belief, all liability for errors and omissions, damage or loss resulting here from is hereby excluded. Recommendations for use should be verified as to suitability and compliance with actual requirements, specifications and any applicable laws and regulations.

BKB House, Goyt Valley Industrial Estate, Off Station Road, Furness Vale, High Peak, SK23 7SN.
Tel 44 (0) 1663 740120 Fax 44 (0) 1663 740121
Registered in England No.2026997 Directors: C.P.Kenyon MD, C.F.Kenyon

AU TOFROTH® is a registered trademark of the BASF Corporation (USA).