

TRIDENT FOAMS LIMITED



TRIPOR TRICAST TANCAST AUTOFROTH AUTOPOR MHD

TRICAST 5 POLYURETHANE FOAM

DESCRIPTION

Tricast 5 is a medium density rigid Polyurethane Foam in sheet form, and is available in scored and pre-cut foam kits for a variety of GRP manufacturing applications. Tricast 5 does not contain any substances alleged to deplete the Ozone Layer, i.e. it is ODP-zero.

Dimensions:	Thickness:	6 - 300mm
	Width:	600, 1200mm
	Length:	600, 1200, 2400
	Other sizes on request.	

TYPICAL PROPERTIES

Nominal density	80 kg/m ³ (5 lbs/ft ³)
Initial thermal conductivity	0.03 W/m ² K @ 23°C (BS874, Anacon)
Closed Cell (BS 4370 Prt 2 Method 10)	> 95%
Compressive Strength (BS.4370 Prt.1 1968 Method 3)	
Normal to major plane	720 kPa
Parallel to major plane	
Tensile Strength (BS.4370 Prt.2 1973 Method 9)	750 kPa
Parallel to major plane	
Cross break strength (BS 4370 Prt.1 method 4)	1000 kPa
Perpendicular to major plane	
Shear Strength (BS.4370 Prt.2 1973 Method 6)	
Parallel to major plane	450 kPa
Upper temperature limit	90°C
Dimensional stability (BS 4370 Prt.1 method 5A)	
70°C for 7 days	<+ 0.5%
50°C / 100%rh for 7days	<+ 0.5%
-20°C for 7 days	No change

APPLICATIONS

Tricast 5 is used as a core material in GRP structures to increase stiffness and for load bearing purposes particularly in the field of boat building. It is also ideal for use in moulding and modelling work.

Whilst the information above is true and accurate to the best of our knowledge and belief, all liability for errors and omissions, damage or loss resulting here from is hereby excluded. Recommendations for use should be verified as to suitability and compliance with actual requirements, specifications and any applicable laws and regulations.

BKB House, Goyt Valley Industrial Estate, Off Station Road, Furness Vale, High Peak, SK23 7SN.
Tel 44 (0) 1663 740120 Fax 44 (0) 1663 740121
Registered in England No.2026997 Directors: C.P.Kenyon MD, C.F.Kenyon

AU TOFROTH® is a registered trademark of the BASF Corporation (USA).