

# TRIDENT

## FOAMS LIMITED



✕TRIPOR ✕TRICAST ✕TANCAST ✕AUTOFROTH ✕AUTOPOR ✕MHD

### TRIPOR 217

'Tripor 217' is a medium density, rigid foam system which may be poured in place to fill cavities. It is ideally suitable for semi structural infill of fibreglass components, and relies on the thorough mixing of two low viscosity liquids by either hand or machine mix techniques. 'Tripor 217' contains no CFC's or HCFC's and therefore has an Ozone Depletion Potential (O.D.P.) of zero.

#### FOAM MANUFACTURE

The foam is produced by the mixing together of the two Components A and B at a ratio of 1 to 1.2 by weight. In hand mixing the Component A should be pre-mixed for at least one minute to aerate it, before mixing with the Component B. After mixing the foam should be immediately transferred to the cavity to be filled, pouring should be finished before there is any significant amount of expansion. The foam should be processed between the temperatures of 18 - 25°C.

The following times are typical for a Quality Control procedure for the checking of cream, string and rise times and measurement of the free rise density. The test is conducted at a temperature of 20°C using 44 grams of Component A and 53 grams of Component B mixed together in a cup of approximately 600 ml. volume, stirred intensively for 15 seconds using a high speed stirrer. Immediately after mixing the chemicals are transferred to a second 600 ml cup.

Mixing Time	15 seconds	
Cream Time	20-30 seconds	(from start of mixing to start of rise)
String Time	110-150 seconds	(from start of mixing to when a thread can be drawn from the rising foam with an inserted rod)
Rise Time	170-220 seconds	(from start of mixing to end of rise)
Tack Free Time	210-260 seconds	(from start of mixing till surface can be lightly touched without foam sticking)
Density (free rise)	75-80 kg/M <sup>3</sup>	(weight of cups contents after removing head, divided by volume of cup)
Core Density (free rise)	70-75 kg/M <sup>3</sup>	(weight of a piece cut from a test block divided by volume of the cut piece)
Ratio	1:1.2	(by weight)

#### STORAGE & HANDLING

It is extremely important that the drums should be re-sealed immediately after use to prevent the entry of moisture which will adversely affect the resultant foam. The shelf life of the materials is four months when stored in sealed drums within the recommended temperature range of 10 - 30°C, but users are recommended not to hold in stock longer than necessary.

#### **PLEASE SEE THE SEPARATE SAFETY DATA SHEETS BEFORE USING THESE PRODUCTS.**

The data contained in this sheet is to our knowledge true and accurate but recommendations are made without guarantee or warranty since application and conditions are outside our control. It is suggested that users should carry out their own tests to ensure 'Tripor' meets their requirements

BKB House, Goyt Valley Industrial Estate, Off Station Road, Furness Vale, High Peak, SK23 7SN.  
Tel 44 (0) 1663 740120 Fax 44 (0) 1663 740121  
Registered in England No.2026997 Directors: C.P.Kenyon MD, C.F.Kenyon

AU TOFROTH® is a registered trademark of the BASF Corporation (USA).